

CEMENTO 3D



CEMENTO 3D

THREE-DIMENSIONAL
DECORATIVE COATING

DEEP MATERIAL EFFECT.
PERSONALITY IN RELIEF.

-  REALISTIC 3D EFFECT
-  EXCLUSIVE DESIGN
-  APPLICABLE ON EXISTING SURFACES
-  HIGH RESISTANCE AND DURABILITY



LIVING ROOM
3D decorative coating
smooth cement effect



BATHROOM
Elegant and contemporary
3D reliefs



KITCHEN
3D coating for design
environments with character



SHOWER
Waterproof, resistant
and easy to clean



EXTERIOR WALLS
Resistant to weathering
and UV rays



HIGH ADHESION ON
EXISTING SURFACES



WATER RESISTANCE
WITH COMPLETE SYSTEM



HIGH MECHANICAL
STRENGTH



SLIP RESISTANCE
CLASS R11



HIGH QUALITY
RAW MATERIALS

NIKKOLOR
ITALIA®

www.nikkolor.net

CEMENTO 3D

DESCRIPTION

Cemento 3D is a next-generation structured nanocement, a premixed powder composed of selected quartz sands and marble powders, minerals, nanoresins, and special additives that provide excellent adhesion to all common substrates, resistant to mold, algae, and bacteria, and, in particular, an extraordinary ability to resist the spread of flames and the development of smoke. The complete Cemento 3D cycle is certified.

FIELDS OF USE

- Ideal for covering floors, walls, and ceilings, both indoors and outdoors
- public and private spaces
- shopping centers, shops, bars, villas, residences
- swimming pools, balconies, terraces, bathrooms, shower stalls, saunas
- kitchens, furniture, and furnishings

The unique feature of the total absence of joints allows for seamless solutions between the floor and the wall, all of which satisfies the furnishing needs of modern and contemporary architecture.

MAIN FEATURES

- Realistic and natural look of nanocement
- Seamless, seamless surface
- Highly resistant and durable
- Can be used on interior and exterior walls, furniture, and decorative panels

PREPARATION, COLORING AND MIXING

- The composition is 6 liters of drinking water in 20 kg of Cemento 3D
- 1. Add water to a clean bucket and pour in the chosen color toner, stirring well.
- 2. Add the Cemento 3D in small doses and mix thoroughly using a mechanical mixer until a smooth, lump-free paste is obtained.

PREPARATION AND APPLICATION

- The substrates must be dry, free from dust, paint, wax, oil and friable parts.
- 1. Apply a single coat of Primer Beton using a stainless-steel trowel, evenly and evenly over the entire surface to be treated.
- 2. Allow the product to dry for 24 hours (+20°C).
- 3. Apply a first coat of Cemento 3D using a stainless-steel trowel.
- 4. Allow to dry for 12 hours (+20°C).
- 5. Apply a second coat of Cemento 3D as described for the first coat.
- 6. Allow to dry for 24 hours (+20°C).
- 7. Apply a first coat of VetroLiquido PRP using a short-haired roller and immediately afterward, lightly smooth the wet product with a trowel.
- 8. Allow to dry for 24 hours (+20°C).
- 9. Apply a second coat of VetroLiquido PRP as described for the first coat.
- 10. Allow to dry for 24 hours (+20°C).
- 11. Apply a third coat of VetroLiquido PRP as described for the second coat.
- 12. Allow to dry for 72 hours (+20°C).

CEMENTO 3D

OTHER INDICATIONS

- It is recommended to avoid direct contact with highly aggressive substances, such as strongly acidic or basic substances and strongly oxidizing substances (e.g., hair dyes), which can alter the color of the flooring.
- Vulcanized plastics with a high plasticizer content (e.g., tires) can mark the floor if left in prolonged contact with the flooring.
- The photographic images in the catalog and on the website, as well as the colors shown in the samples, are to be considered purely indicative.
- Use materials from a single production batch for each project.
- Materials from different batches may

WARNINGS

- Product for professional use. Comply with national standards and regulations.
- Apply when the substrate temperature is above +10°C.
- Apply to permanently dry substrates.
- Protect from direct sunlight and drafts for the first 6 hours.
- Do not apply to dirty or loose surfaces.
- Dispose of in accordance with applicable regulations.
- Materials exposed to temperature changes (due to transportation, storage, construction site, etc.) may cause substantial changes to the product (e.g., crystallization, partial hardening, fluidification, accelerated or delayed curing).
- In most cases, restoring the products to optimal conditions will also restore their original characteristics.
- Protect surfaces and objects in the application area from accidental contact.
- If necessary, request the safety data sheet or contact Nikkolor Italia Technical Customer Service at +39 333 861 8963.
- www.nikkolor.net

TECHNICAL DATA

- Appearance: Powder
- Color: White
- Colors obtainable with toner: 32 shades
- Dilution: ~300 ml of drinking water per kg of product
- Mixture pH: 12
- Coverage: 16 m² with two coats
- Pot Life: 4 hours at +20°C
- Grain Size: Max 0.3 mm
- Mineralogical nature of the aggregate: Silicon/carbonate
- Consistency: Thixotropic
- Density of the mix: 1,500 kg/m³
- Packaging: 20 kg
- Apparent density: 1.20 kg/L
- Apparent density of the mix: 1.50 kg/L
- Optimal application temperature: (*) +5°C to +30°C
- Operating temperature and thermal resistance: -30°C to +70°C
- Surface drying: 3 hours at +20°C

CEMENTO 3D

- Drying time for the second coat: 12 hours at +20°C
- Drying time for walking: 48 hours at +20°C
- Full hardening: ~7 days at +20°C
- Laying of tables, chairs, and furniture: ~10 days at +20°C
- Full curing time: 28 days at +20°C
- Water and UV resistance after application of VetroLiquido PRP: ~7 days
- Shelf life: 24 months from the date of production in the original, unopened packaging
- Packaging: 20 kg
- End use classification (UNI EN 1062.1 – 4.1): Decoration and protection
- UFI Code: NC00-Y08C-J00G-9N29

PERFORMANCE CHARACTERISTICS

- Tensile strength (EN 13892-2): 38 N/mm² after 28 days
- Compressive strength (EN 13892-2): 38 N/mm² after 28 days
- Flexural strength (EN 13892-2): 36 Nm after 28 days
- Impact resistance (UNI EN ISO 6272-1): 0.500 Nm/501 m
- Permeability resistance (UNI EN 1062-3): 0.0001 kg/m²*h^{0.5} after 5 days
- Reaction to fire (EN 13501-1) CLASS 1 after 28 days
- Adhesion strength to concrete (EN 13892-8): 6 N/mm² after 28 days
- Determination of the chair with rubber wheels (EN 425): absolutely free of defects
- Commissioning service (R11 system) ≈ 48 h / ≈ 7 days (contact with water)

Data collected at +20°C, 65% RH, and no ventilation. They may vary depending on specific construction site conditions: temperature, ventilation, and substrate absorbency.

This information is current as of January 2026 and may be subject to additions and/or changes over time by Nikkolor Italia s.r.l. For any such updates, please consult the website www.nikkolor.net.

Nikkolor Italia s.r.l. is therefore responsible for the validity, timeliness, and currency of its information only if taken directly from its website.

The technical data sheet is prepared based on our best technical and application knowledge.

However, since we cannot directly influence construction site conditions and the execution of work, it represents general information that does not bind our company in any way.

A preliminary test is therefore recommended to verify the product's suitability for the intended use.

CEMENTO 3D

RULES AND TIPS

Let's start by saying that the success of a floor depends largely on the substrate, the correct application method, and the mixing and installation phases. However, proper cleaning and proper maintenance of the floor is the responsibility of those who live with seamless surfaces. The more it is cared for, the longer the floor will last.

Advantages of Cemento 3D Flooring

The flooring is available in a wide variety of colors and textures, can be matte or satin, smooth or rough, and is highly resistant to wear, trampling, and impact. Furthermore, it stands up well to humid environments, has good fireproofing properties, thus preventing the spread of flames, and is highly resistant to chemicals. The surface is hygienic because it has no joints or seams, and, finally, it is easy to clean and maintain.

Disadvantages of Cemento 3D Flooring

The floor is indeed resistant, but not as much as a ceramic or stoneware floor. It can be repaired rather than completely replaced if the damage affects a very small portion of the surface, and this is also a plus, but in any case, it must be installed by qualified professionals. It is not suitable for DIY.

Using the Cemento 3D Floor

In the first week after applying the complete cycle, it is very important not to clean the floor under any circumstances. Avoid spilling any liquid on the floor that could alter the color, lighten, or even bleach it. Avoid walking on the floor at all costs, as it has not yet reached its maximum hardness and chemical resistance.

Cleaning the Cemento 3D Floor

Start cleaning the floor by removing dust and dirt using a soft-bristled broom or a vacuum cleaner, gently sweeping the surface. Be sure to cover the entire floor, including hard-to-reach areas such as corners. Mopping the floor without sweeping away dust and dirt can damage the surface layer over time, leaving it looking dirty even after thoroughly mopping.

Helpful tips for cleaning Cemento 3D flooring

Prepare a solution of warm water and neutral soap following the manufacturer's instructions. Using a microfiber cloth, thoroughly clean the entire surface. Be sure not to overuse the detergent, as too much could leave residue on the floor. Neutral products are the best choice for interiors and home environments; they're simple, economical, and extremely effective.

Helpful tips on how to treat Cemento 3D flooring

- Use a doormat outside the door
- Use non-absorbent mats under the sink and washbasin
- Use cotton or natural fiber mats; those made of rubber or synthetic fibers may release oil and stain the surface
- Place shock-absorbent felt pads under the legs of chairs, tables, desks, and furniture
- Use silicone rubber casters for office chairs

CEMENTO 3D

- Clean up any spilled liquids immediately; if left to settle, they could damage the floor's surface protection.
- Be extremely careful not to spill anything on the surface, such as oils, perfumes, creams, greases, fillers, mortars, and paints, which could permanently damage the floor.
- Do not leave damp cloths on the floor.
- Do not use abrasive or aggressive products such as wire brushes, sandpaper, hydrochloric acid, acetone, or ammonia, as their corrosive properties could damage the floor.
- Be extremely careful when assembling furniture (in any case, it is recommended to let the surface fully cure) and do not place objects on the floor. In fact, improperly curing the floor will result in unsightly stains appearing even after several days.
- Do not drag any objects across the floor.
- Walk only with clean shoes.
- Avoid standing water and direct contact with moisture.
- Knowledge of the substrates and their suitability for the correct installation method and use of the products is the responsibility of the person performing the work.
- Proper treatment, maintenance, and cleaning of the surfaces is the customer's responsibility.

However, since we cannot intervene directly, the company assumes no responsibility for the conditions of the construction sites, the execution of the work, or the proper treatment, maintenance, and post-installation cleaning of the floors, as these are beyond our control. For any information, please contact our technical support team.

